

Induction Braze Copper Tube to Brass Fitting

United Induction Heating Machine Limited

We are experienced in Induction Heating, induction heating machine, Induction Heating equipment. They are widely used in induction heating service, induction heat treatment, induction brazing, induction hardening, induction welding, induction forging, induction quenching, induction soldering, induction melting and induction surface treatment applications
<http://www.uihm.com>

Objective To use induction heating to braze a copper tube to a brass fitting using a preform braze wire. Processing is to occur under an atmosphere of Nitrogen and 4% Hydrogen gas. The braze preforms melt at 1190°F, but the parts need to be kept below 1300°F. The parts need to be processed at a rate of 175 to 200 per hour which translates into 18 seconds of heating time per part.

Material Copper Tubing Measuring 0.5" OD and 2" Long, Brass fitting, Braze Preform, No Flux.

Temperature Above 1190°F but not to exceed 1300°F

Frequency 133 kHz

Equipment Power of 6kW output solid state induction heating power supply with three (3) busses, eight (8) capacitors totaling 0.66 μ F, and a unique four turn helical coil.

Process Power of 6KW output solid state power supply along with a unique four turn helical coil were used to achieve the following results.

Results • The requested atmosphere was provided under a bell jar by supplying 95% Nitrogen/5%Hydrogen at a rate of 25-30 cfh.

• A heating cycle of only 10 seconds was necessary to attain sufficient braze flow which surpasses the required limit of 18 seconds

Braze-Copper-Tube

service@uihm.com

United Induction Heating Machine Limited

Copper Tube

